PRODUCT SPECIFIC DATA:

WILLIAMSPORT
SOLID - SKU #PL-750118
ENGINEERED - SKU #PL-625118

SPECIES:	**Black Walnut**
CUT:	Plain Sawn
GRADE:	Select/Better
FINISH:	Hardwax Oil
Janka Hardness (ASTM D 1037):	1,010
Flame Spread Class Rating (ASTM E 84):	Class III (C)
Flame Spread Index (ASTM E 84):	130-140

NEWPORT
SOLID - SKU #PL-750130
ENGINEERED - SKU #PL-625130

SPECIES:	**Black Walnut**
CUT:	Plain Sawn
GRADE:	Character
FINISH:	Hardwax Oil
Janka Hardness (ASTM D 1037):	1,010
Flame Spread Class Rating (ASTM E 84):	Class III (C)
Flame Spread Index (ASTM E 84):	130-140

STOCKPORT
SOLID - SKU #PL-750119
ENGINEERED - SKU #PL-625119

SPECIES:	**Black Walnut**
CUT:	Rift & Quarter Sawn
GRADE:	Select/Better
FINISH:	Hardwax Oil
Janka Hardness (ASTM D 1037):	1,010
Flame Spread Class Rating (ASTM E 84):	Class III (C)
Flame Spread Index (ASTM E 84):	130-140

BRIDGEPORT
SOLID - SKU #RM-750528
ENGINEERED - SKU #RM-625528

SPECIES:	**Black Walnut (UNSTEAMED)**
CUT:	Origianl Cut
GRADE:	Character
FINISH:	Hardwax Oil
Janka Hardness (ASTM D 1037):	1,010
Flame Spread Class Rating (ASTM E 84):	Class III (C)
Flame Spread Index (ASTM E 84):	130-140

Note: BRIDGEPORT black walnut is unsteamed.

HARBOR
SOLID - SKU #BS-750607
ENGINEERED - SKU #BS-625607

SPECIES:	**Black Walnut**
CUT:	Oriignal Cut
GRADE:	Character Grade
TREATMENT:	Textured Surface
FINISH:	Hardwax Oil
Janka Hardness (ASTM D 1037):	1,010
Flame Spread Class Rating (ASTM E 84):	Class III (C)
Flame Spread Index (ASTM E 84):	130-140

For WILLIAMSPORT, NEWPORT, STOCKPORT, BRIDGEPORT and HARBOR:

STANDARD MILLWORK:
Tongue & Groove, Endmatched

STANDARD DIMENSIONS & EDGE DETAIL:

	Solid	Engineered
Thickness:	3/4″	5/8″ (4 mm wear layer)
Width:	5″	5″
Random Lengths:	2′-10′	2′-10′
Edges:	Microbevel	Microbevel

Note: Additional widths and lengths available upon request.

FINISH SPECS: Hardwax Oil

FLASH POINT	ASTM D 93: > 215°F (PenskyMartens)
RESISTANCE TO WATER	(NEN-EN 13442): no visual or tangible changes.
RESISTANCE TO WEAR	(NEN 2072 – Taber Abraser en CS 17 sanding wheels): strong absorption basantol liquid, only after 800 to 1000 rotations.
RESISTANCE TO HEAT	Until 212 °F

SUSTAINABLE ATTRIBUTES:

CERTIFICATION	Available as FSC-Certified
POSSIBLE LEED CREDITS	MR 5 - Regional Materials MR 6 - Rapidly Renewable Resource (Hardwax-Oil Finish) MR 7 - Certified wood EQ 4.1 - Low-emitting materials: Adhesives & Sealants (Hardwax-Oil Finish) EQ 4.2 - Low-emitting materials: Paints & Coatings (Hardwax-Oil Finish) EQ 4.4 - Low-emitting materials: Composite Wood & Agrifiber Products (Engineered)

Photo Disclaimer: Project and product photos are meant to be a general guide to product appearance only. Due to our handcrafted process and wood being a product of nature, the color, grain pattern, character and profile will vary between individual boards on a project and will never be an exact match.

Janka Rating from similarly tested products - expected to be close to actual measurements of reSAWN TIMBER co.'s products.
Data from Forest Products Laboratory (FPL) General Technical Report (GTR) 190 - expected to be close to actual measurements of reSAWN TIMBER co.'s products.

KURUMI
BLACK WALNUT
SOLID - SKU #CH-750213

SPECIES:	**Black Walnut**
CUT:	Oriignal Cut
GRADE:	Character Grade
FINISH:	CHARRED, Conversion Varnish
Janka Hardness (ASTM D 1037):	1,010
Flame Spread Class Rating (ASTM E 84):	Class III (C)
Flame Spread Index (ASTM E 84):	130-140

NOTE: SOLID ONLY

LONGPORT
BLACK WALNUT
ENGINEERED - SKU #WA-625000
SOLID - SKU #WA-750000

SPECIES:	**Black Walnut**
CUT:	Oriignal Cut
GRADE:	Character Grade
FINISH:	Matte Polyurethane
Janka Hardness (ASTM D 1037):	1,010
Flame Spread Class Rating (ASTM E 84):	Class III (C)
Flame Spread Index (ASTM E 84):	130-140

STANDARD DIMENSIONS & EDGE DETAIL:

	Solid - KURUMI /LONGPORT	Engineered - LONGPORT
Thickness:	3/4″	5/8″ (4 mm wear layer)
Width:	5″	7″
Random Lengths:	2′-10′	2′-10′
Edges:	Microbevel	Microbevel

Note: Additional widths and lengths available upon request.

INSTALLATION GUIDE:

	Solid	Engineered
Above-grade	YES	YES
On-grade	YES	YES
Below-grade	**NO**	YES
Over Radiant Heat	YES	YES

ACCEPTABLE SUB-FLOORS and INSTALLATION METHODS - see installation guidelines for additional details and recommended adhesive**:**
Plywood Sub-floor : Glue-down, Nail-down, Staple-down
Concrete Sub-floor: Glue-down

SUSTAINABLE ATTRIBUTES:

CERTIFICATION	Available as FSC-Certified
POSSIBLE LEED CREDITS	MR 5 - Regional Materials MR 7 - Certified wood EQ 4.4 - Low-emitting materials: Composite Wood & Agrifiber Products (Engineered)