PRODUCT SPECIFIC DATA:



HERITAGE

HERITAGESPECIES:Antique Reclaimed Oak (Mix of Red/White Oak)GRADE:RusticFINISH:Matte Polyurethane/UnfinishedJanka Hardness (ASTM D 1037):1,325 *Flame Spread Class Rating (ASTM E84):Class III (C) **Standard Millwork:Tongue & Groove, Endmatched

HERITAGE is a mix of reclaimed red & white oak creating a pleasing variation of colors. Expect a warm palette of colors, with dense & varying grain patterns. Typical character marks include mineral staining, color changes, weathering, checking, nail holes, and knots. Available SOLID or ENGINEERED.

APPLICATIONS: HERITAGE is for INTERIOR applications - walls, ceilings, millwork and flooring (not recommended for exterior applications)

* Janka Rating from similarly tested products - expected to be close to actual measurements of reSAWN products.

** Flame Spread Class Rating, Flame Spread Index Data and Smoke Developed Index based on report from American Wood Council - 2017. Testing is on unfniished, solid wood - see attached for additional details. reSAWN's products are not tested but are expected to be close to actual measurements for comparable wood species -- can be treated to Fire Treated to Class A for Interior Applications - please call to inquire.

Photo Disclaimer: Project and product photos are meant to be a general guide to product appearance only. Due to our handcrafted process and wood being a product of nature, the color, grain pattern, character and profile will vary between individual boards on a project and will never be an exact match.

reSAWN TIMBER co.

resawntimberco.com

P 215 709 2001

reSAWN TIMBER co.[™] The Value of a Natural Product is Without Equal.[™]

RECLAIMED WOOD Tech Specs



OLD SCHOOL

OLD SCHOOL

SOURCE: Reclaimed Oak Barn Siding - Skip Planed

Janka Hardness (ASTM D 1037): 1,325 *

Flame Spread Class Rating (ASTM E84): Class III (C) **

OLD SCHOOL begins as WEATHERWORN and goes thru an additional step called "skip planing". Skip planing is a process whereby the boards are put thru a planer set to only remove the high points, "skipping" over the low points to create contrast. Typical character marks include mineral staining, color changes, weathering, checking, nail holes, knots, and heavy patina. Available in SOLID and ENGINEERED. Call to discuss custom lengths and widths. Due to the nature of this material, thicknesses tend to vary slightly. Available unfinished or prefinished with a matte polyurethane.

APPLICATIONS: OLD SCHOOL is for INTERIOR and EXTERIOR applications - walls, ceilings, and

millwork (not recommended for flooring)

HERITAGE, WORMWOOD, JAVELIN, OLD SCHOOL - STANDARD DIMENSIONS & EDGE DETAIL:

	Solid	Engineered
Thickness:	3/4″	5/8" (4 mm wear layer)
Width:	5″	5″
Random Lengths:	2'-10'	2'-10'
Edges:	Microbevel	Microbevel

* Janka Rating from similarly tested products - expected to be close to actual measurements of reSAWN products.

** Flame Spread Class Rating, Flame Spread Index Data and Smoke Developed Index based on report from American Wood Council - 2017. Testing is on unfniished, solid wood - see attached for additional details. reSAWN's products are not tested but are expected to be close to actual measurements for comparable wood species -- can be treated to Fire Treated to Class A for Interior Applications - please call to inquire.

Photo Disclaimer: Project and product photos are meant to be a general guide to product appearance only. Due to our handcrafted process and wood being a product of nature, the color, grain pattern, character and profile will vary between individual boards on a project and will never be an exact match.

reSAWN TIMBER co.[™] The Value of a Natural Product is Without Equal.[™]

RECLAIMED WOOD Tech Specs

BARN GREY

BLACK & TAN

BUCOLIC BLANC

REED

al si	and the second s	
		Ac
		allin

BARN GREY, BLACK & TAN, BUCOLIC BLANC, REED, & KINOKO **SPECIES: Reclaimed Hemlock** GRADE: Rustic FINISH: STAIN/SEALER (NOTE: REED IS UNFINISHED) lanka Hardness (ASTM D 1037): 500 * Flame Spread Class Rating (ASTM E84): Class II (B) ** Flame Spread Index (ASTM E84): 35 ** Smoke Developed Index (ASTM E84): 175 ** **S**3S Standard Milling:

KINOKO

BARN GREY, BLACK & TAN, BUCOLIC BLANC & KINOKO feature antique reclaimed hemlock that has been wirebrushed to accentuate the unique grain pattern of hemlock and finished with a stain/sealer. REED is standardly antique reclaimed hemlock that is brushed and UNFINISHED. Thickness, width and lengths may vary due to the nature of this reclaimed material. Standard milling is square edge; available with Tongue & Groove upon request.

APPLICATIONS: reSAWN's Reclaimed Hemlock is for INTERIOR applications - walls, ceilings, and millwork (not recommended for flooring or exterior applications)

STANDARD DIMENSIONS, MILLING & EDGE DETAIL:

	Solid
Thickness:	+- 7/8″
Width:	7″
Random Lengths:	4'-12'
Edges:	Square

* Janka Rating from similarly tested products - expected to be close to actual measurements of reSAWN products.

** Flame Spread Class Rating, Flame Spread Index Data and Smoke Developed Index based on report from American Wood Council - 2017. Testing is on unfniished, solid wood - see attached for additional details. reSAWN's products are not tested but are expected to be close to actual measurements for comparable wood species -- can be treated to Fire Treated to Class A for Interior Applications - please call to inquire.

Photo Disclaimer: Project and product photos are meant to be a general guide to product appearance only. Due to our handcrafted process and wood being a product of nature, the color, grain pattern, character and profile will vary between individual boards on a project and will never be an exact match.

PRODUCT SPECIFIC DATA:



WEATHERWORN

WEATHERWORN

SOURCE:

Reclaimed Barn Siding

WEATHERWORN does not have a finish applied as the boards have been naturally oxidized over the years to produce a tough, weather resistant "skin". Typical character marks include mineral staining, color changes, weathering, checking, nail holes, knots, and heavy patina. Available in SOLID ONLY. Call to discuss custom lengths and widths. Due to the nature of this material, thicknesses tend to vary slightly.

	Solid
Thickness:	+/- 1/2"
Random Widths:	3-3/4", 4-1/4", 5-1/4", 6-1/4" random widths
Random Lengths:	4'-12'
Edges:	Square
Milling:	S3S
ADDITIONIC WEATHEDWOOD IS (STINTEDIOD STATEDIOD STATEDIOD	

APPLICATIONS: WEATHERWORN is for INTERIOR and EXTERIOR applications - walls, ceilings, and millwork (not recommended for flooring)

PERLINO SOURCE:

Reclaimed Barn Siding

PERLINO is ANTIQUE RECLAIMED BARN SIDING – for interior wall cladding. PERLINO has been wirebrushed and finished with a stain/sealer. Expect lots of texture and variation to the grain. Typical character marks include mineral staining, color changes, weathering, checking, nail holes, and knots. Due to the nature of this material, thicknesses tend to vary slightly.

	Solid
Thickness:	+/- 1/2"
Random Widths:	3-3/4", 4-1/4", 5-1/4", 6-1/4" random widths
Random Lengths:	4'-12'
Edges:	Square
Milling:	S3S
ADDITCATIONS. DEDITING	is for INTERIOR applications, walls, sailings, and mil

APPLICATIONS: PERLINO is for INTERIOR applications - walls, ceilings, and millwork (not recommended for flooring)



SHETLAND

PERLINO

SHETLAND SOURCE:

Reclaimed Barn Siding

SHETLAND is ANTIQUE RECLAIMED BARN SIDING – for interior wall cladding. SHETLAND has been wirebrushed and finished with a stain/sealer. Expect lots of texture and variation to the grain. Typical character marks include mineral staining, color changes, weathering, checking, nail holes, and knots. Due to the nature of this material, thicknesses tend to vary slightly.

	Solid
Thickness:	+/- 1/2"
Random Widths:	3-3/4", 4-1/4", 5-1/4", 6-1/4" random widths
Random Lengths:	4'-12'
Edges:	Square
Milling:	S3S
APPLICATIONS: SHETLAND is fo	r INTERIOR applications - walls, ceilings, and millwork (not

recommended for flooring)

* Janka Rating from similarly tested products - expected to be close to actual measurements of reSAWN products.

** Flame Spread Class Rating, Flame Spread Index Data and Smoke Developed Index based on report from American Wood Council - 2017. Testing is on unfniished, solid wood - see attached for additional details. reSAWN's products are not tested but are expected to be close to actual measurements for comparable wood species -- can be treated to Fire Treated to Class A for Interior Applications - please call to inquire.

Photo Disclaimer: Project and product photos are meant to be a general guide to product appearance only. Due to our handcrafted process and wood being a product of nature, the color, grain pattern, character and profile will vary between individual boards on a project and will never be an exact match.

reSAWN TIMBER co.

resawntimberco.com

P 215 709 2001

vers 6/23