

## MATSU 2.0 PROTECTOR TECH SPECS

MATSU 2.0 denotes Accoya wood that will require the installer to apply a top coat of finish post-install. This finish will be included on the sales order and shipped with the materials.

### EXTERIOR ONLY FINISH:



**MATSU 2.0**

### PRODUCT SPECIFICATIONS:

**Ingredients:** Water, refined plant oil, medium oil alkyd, zinc & lead free driers, low VOC co-solvent, moldicide, earth oxide pigment.

**VOC content:** <85g/L.

**Coverage:** 1 COAT applied on site: approx. 75 sf per liter.

### PRODUCT HANDLING:

- Store with lid tightly closed in a cool place with ambient temperature min 41°F - max 104°F.
- Clean up with water. Keep out of drains and waterways.
- Soak cloths in warm soapy water, rinse and hang to dry as they may self ignite if left unattended.
- Keep out of reach of children. Use in a well ventilated area. If swallowed, seek medical advice.

### FLASH POINT:

>140°F. (Non-DG for transport).

Full SDS available on request.

## INSTRUCTIONS FOR APPLYING WATERBORNE EXTERIOR OIL ON PREFINISHED ACCOYA CLADDING:

These instructions are for MATSU 2.0 materials that will require the installer to apply a top coat of finish, post-install.

### SITE CONDITIONS:

1. Ensure timber surfaces are clean, dry, and free from saw dust or metal filings. DO NOT apply oil to timber where the moisture content is above 16%.
2. Only work when weather conditions are dry. Make sure the weather will remain without precipitation for at least 48 hours to allow the coating to dry.
3. Never apply in direct sunlight or at temperatures under 41°F (5°C).
4. Do not cover and do not place heavy objects on the wood until completely dry.

### APPLICATION:

1. Shake/stir finish well prior to and during use ensuring all pigment is agitated. Do **not** thin product.
2. **POST INSTALL COAT:** A coat should be applied post-install working from the bottom of the structure and moving up. Apply one thin even coat with a brush or applicator pad to the face of the planks. Maintain a wet edge to avoid lap marks. Start with a less visible area and test to establish technique.
3. **OF NOTE:**
  - This is a penetrating stain, unevenness in the timber grain, surface preparation and or application will result in differential appearance. Apply evenly and do not allow overlapping areas to dry during application.

### MAINTENANCE:

Refer to reSAWN TIMBER co.'s weathering and maintenance guidelines for post-install care.

### PACKAGING:

- 4 liters
- 10 liters (special order - subject to availability)